

Technical data sheet PVA

Ultimaker

Chemical name	Polyvinyl alcohol
Description	PVA (polyvinyl alcohol) is a water soluble support material for multi-extrusion 3D printing. With a good thermal stability, Ultimaker PVA is ideal for printing complex models that require supports for large overhangs, deep internal cavities, and intricate geometries. Designed for a seamless 3D printing experience, our PVA provides good adhesion to both PLA and Nylon.
Key features	Good thermal stability resulting in better degradation resistance compared to other PVA filaments; less moisture sensitive than other PVA filaments; great adhesion to both PLA and Nylon; safe dissolution in tap water (no harmful chemicals required); biodegradable with no hazardous by-products.
Applications	Reliable 3D printing of water soluble support structures for PLA and Nylon build materials. PVA molds
Non-suitable for	Reliable 3D printing of water soluble support structures for ABS or CPE build materials

Filament specifications

	<u>Value</u>	<u>Method</u>
Diameter	2.85±0.10 mm	-
Max roundness deviation	0.10 mm	-
Net filament weight	350 g / 750 g	-
Filament length	~45 m / ~96 m	-

Color information

	<u>Color</u>	<u>Color code</u>
	Natural	n/a

Mechanical properties (*)

Injection molding

3D printing

	Typical value	Test method	Typical value	Test method
Tensile modulus	3860 MPa	ISO 527 (1 mm/min)	-	-
Tensile stress at yield	-	-	-	-
Tensile stress at break	78 MPa	ISO 527 (50 mm/min)	-	-
Elongation at yield	-	-	-	-
Elongation at break	9.90 %	ISO 527 (50 mm/min)	-	-
Flexural strength	-	-	-	-
Flexural modulus	-	-	-	-
Izod impact strength, notched (at 23°C)	-	-	-	-
Charpy impact strength, unnotched (at 23°C)	1.6 kJ/m ²	ISO 179	-	-
Hardness	-	-	-	-

Thermal properties

Typical value

Test method

Melt mass-flow rate (MFR)	17-21 g/10 min	(190 °C, 21.6 kg)
Heat deflection (HDT) at 0.455 MPa	-	-
Heat deflection (HDT) at 1.82 MPa	-	-
Vicat softening temperature at 10N	60.2 °C	ISO 306
Glass transition	-	-
Coefficient of thermal expansion	-	-
Melting temperature	163 °C	ISO 11357
Thermal shrinkage	-	-

Other properties

Typical value

Test method

Specific gravity	1.23	ASTM D1505
Flame classification	-	-

(*) See notes.

Notes

Properties reported here are average of a typical batch. Ultimaker is constantly working on extending the TDS data.

Disclaimer

Any technical information or assistance provided herein is given and accepted at your risk, and neither Ultimaker or its affiliates make any warranty relating to it or because of it. Neither Ultimaker nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of Ultimaker's conditions of sale. Specifications are subject to change without notice.

Version

Version 3.010

Date

16/05/2017

Ultimaker